



# Extra Professionale

Water-based Painting for internal use with high cladding power

CODE 1007 - 1008



### COLOUR

36 dyes from colours chart – more than 170 colourings from Plastimur swatch book. Moreover, with the new tintometer colorization system, it is possible to obtain countless paints.

### PACKAGING

Drums litographed of lt 4 and 13

### STORAGE

12 months at least in its original packaging far from low and high temperatures

### CHARACTERISTICS

It is a water-based painting for internal use, opaque, transpiring, washable, with high cladding power, excellent degree of whiteness, composed of resins in water emulsion, micronized charges, specific admixtures, resistant to moulds attack.

### APPLICATION FIELDS

Painting of all internal surfaces, new one or already treated with similar paints, suitable for painting of substrates in gypsum, plasterboard, cementitious or lime based. It has got a good cladding, transpiration and resistance.

### APPLICATION PROCEDURE

#### SUBSTRATES PREPARATION

Substrates have to be fine-finished, cured, perfectly clean, in good conditions, with no detaching parts, oil, grease, dust, humidity, saltpetre or moulds traces. Eventual crumbling surfaces need to be previously consolidated before the product application.

#### PRODUCT PREPARATION

Dilute EXTRA PROFESSIONALE with 40% of clean water for the first coat, 28-30% for the second one, mixing the product with a drill at a low speed rotations, obtaining a dough homogeneous.

#### PRODUCT APPLICATION

Apply in two or more coats, through brush, wool roller or spray, after application of insulating fixative ALBURESIN, after at least 12-24 hours in normal conditions of temperatures and humidity. Apply the product at temperatures between +5°C and +30°C. Do not apply with UR higher than 85%.

rev. 03 del 30.09.2016

### CONSUMPTION

About 0,150 - 0,180 Lt / mq

### TECHNICAL DATA

#### PRODUCT IDENTIFICATION DATA

<b>Consistency</b>	Liquid dense
<b>Colour</b>	36 dyes from colours chart – more than 170 colourings from Plastimur swatch book. Moreover, with the new tintometer colourization system, it is possible to obtain countless paints.
<b>Density of the paste</b>	1,540 kg/lt
<b>Brilliance</b>	Opaque

#### APPLICATION DATA

<b>Dilution ratio</b>	40% for the first coat 28-30% for the second one
<b>Waiting time between coats</b>	6/8 hours
<b>Time to drying for touch</b>	about 2 hours
<b>Drying time</b>	24-36 hours basing on the environmental temperature and substrate's absorption

Tested at +23°C and 50% U.R. in absence of ventilation. Data can change basing on specific conditions in building site.

#### FINAL PERFORMANCE

Resistance to chemical attacks: excellent to atmospheric agents and smog.

### ITEM SPECIFICATION

Decoration and protection of internal surfaces with white or coloured painting EXTRA PROFESSIONALE of Plastimur s.r.l., composed of resins in water emulsion, micronized charges, specific admixtures. This painting is to apply in two coats, after application of fixative "Alburesin", dilute with 40% for the first coat, 28-30% for the second one, with an average consumption of 0,150-0,180 lt/mq.